Specification

Method for Immobilizing Molecules on Surfaces

METHOD FOR IMMOBILIZING MOLECULES ON SURFACES

BACKGROUND OF THE INVENTION

The present invention relates <u>in general</u> to a method for immobilizing compounds, <u>and</u> in particular <u>to the immobilization of molecules</u>, such as for example biomolecules, on surfaces or solid supports.

Chip packaging techniques in which a plurality of ICs (integrated circuits) are housed in one package are known in the prior art. In the stacked-die structure, for example, interlayers made of polymers are frequently employed, which The interlayers effect the connection of the ICs stacked one on another and at the same time help in mechanically protecting the top of the lower chip, which may be sensitive under some circumstances. In some factories the production of such layers is part of the mass production process and, in particular, the thicknesses of such layers can be accurately controlled within the range of a few microns and even less.

In many biochemical and biotechnological applications it is useful to immobilize biomolecules on solid supports. Crosslinkers that effect a connection between the inorganic layer and the biomolecules are commonly employed for bioconjugation on inorganic substrates. In <u>European patent specification</u> EP 1132739 B1, for example, a method is disclosed that serves, in bioconjugation, to bind molecules to inorganic substrates using crosslinkers, <u>with silanes being among the candidates for such crosslinkers</u>. <u>Further-Also proposed in EP 1132739 B1 is a linker system that can be used for the detection and isolation of biomolecules and as a component of a</u>

sensor chip or biochip or as a diagnostic instrument. Thus, in biochemical process sequences for example, an immobilized enzyme can be employed repeatedly. Furthermore, the immobilization of enzymes and other biomolecules is a key technology in the development of biocompatible implants.

In all a A plurality of methods are known for binding molecules, for example biomolecules, to surfaces of supports. In the field of immunology, for example, polystyrene surfaces such as PolySorp and MaxiSorp are used to bind or conjugate biomolecules to surfaces.

From <u>European patent specification</u> EP 0646-038 <u>B1</u> it is known to produce passivated and stabilized porous supports and employ them for bioconjugation. These supports have a high reversible sorption capacity that essentially does not go along with nonspecific adsorption of molecules such as for example proteins, polysaccharides, or oligo- or polynucleotides.

German patent application DE 100 04 884 describes a method for emplacing biomolecules on surfaces using linker-like groups. The method includes bringing the polymer having linker-like groups into contact with a source of hydroxide ions, so that biomolecules such as for example heparin can be applied to substrate surfaces.

In relation to bioconjugation, two <u>relevant issues are the number of main questions are</u> relevant to the individual skilled in the art:

- (i) how many molecules that in all-bind to a well-defined surface, and the number of
- (ii) how many molecules that still display activity after the process of binding.

The known methods of bioconjugation have the disadvantage that linkers are used to bind the molecules to the support. The presence of the linkers disadvantageously reduces the activity of the bound molecules. What is more Further, the known methods are time-consuming and expensive, because of the use of linkers or the corresponding analogs, expensive.

The technical problem underlying the present invention is to furnish What is needed is a

method that makes possible the conjugation or immobilization of biomolecules on a surface in <u>an</u> easy and economical fashion manner, and wherein the activity of the bound molecules is preserved to the greatest extent.

This goal is achieved with a method according to the features of Claim 1. Advantageous developments of the invention are the subject of the dependent claims.

SUMMARY OF THE INVENTION

In the <u>a</u> method according to the invention for immobilizing molecules on <u>a</u> surfaces, a layer of a hydrophobic and, in <u>a</u> particular <u>example</u>, <u>a</u> non-swelling polymer <u>may</u> is to be applied to the surface and molecules are to be immobilized on a surface of the polymer layer.

Such hydrophobic polymers <u>may</u> are, for example, <u>be</u> polyimide or polystyrene. The surface to which the polymer layer is applied <u>may</u> is <u>preferably be</u> made of an inorganic material such as for example a semiconductor material, in particular silicon, a semiconducting oxide, in particular silicon dioxide, glass, nitride, or ceramic.

Hydrophobic polymers such as polyimide or polystyrene have <u>anthe</u> advantage <u>in</u> that they can be applied to the surface of an inorganic support with conventional methods known in semiconductor technology. What is more Further, they electrically insulate the support with respect to the molecules applied to the surface of the polymer layer or substances associated with these molecules. Thus, electrical sensors and processor circuits can be integrated into the support, <u>which may be made</u> for example of a semiconductor material, without any detrimental effect on their function due to molecules and substances applied to the surface of the polymer layer.

In the method-according to the invention, the surface of the support can be completely or only partly covered with the organic hydrophobic polymer. Typical masking processes found usual in the

semiconductor industry <u>may be used being usable in order</u> to hold back parts of the surface. In this way, electrical connection contacts (bonds) can later be emplaced on the support, for example on a chip. It is also possible to hold back parts of the surface for other reasons, thereby and so leavinge regions of the surface, which <u>may beis</u> inorganic if appropriate, uncovered or, conversely, to coat with the polymer only such definite locations of the surface on which molecules, for example biomolecules, can later adhere.

For immobilization, the polymer layer is, for example, brought into contact with organic molecules that can form a compound with the polymer layer. The act of bringing into contact is effected in such a manner fashion—that the molecules are bound in a positionally specific fashionmanner.

Sensor elements are may preferably be integrated into the support under the surface to which the polymer layer is applied, in order so that measurements can be performed on the molecules immobilized on the surface of the polymer layer. These measurements can serve for example to characterize the properties of the biomolecules or chemical reactions that take place in their surroundings.

For example, antibodies can be well bound to surfaces of hydrophobic polymer layers made for example of a polyimide or a polystyrene, with which semiconductor articles or semiconductor layers serving as the support can easily be coated. This way, so that classical detection reactions such as for example ELISA reactions can be carried out subsequently.

Molecules in connection with the present invention are, in particular examples, peptides, proteins, genes and their fragments, nucleic acids, carbohydrate structures such as sugars, cells and their fragments, cell membrane constituents, and/or hormones. Microorganisms, cell extracts, ligands, antigens, antibodies, receptors, lectins, glycopeptides, and/or lipids can naturally also be

immobilized as the molecule on the surface of the polymer layer. The microorganisms can be live or dead microorganisms, live microorganisms in the context of the invention including both growing and also resting cells. The microorganisms can be pre-immobilized by intracellular crosslinking of the cells on the support, the term "pre-immobilization" being understood to refer, for example, to all methods that can lead to fixation of the molecules or cells before immobilization by the method according to the invention. Biopolymers such as for example polysaccharides or proteins or also synthetic polymers are, for example, expediently employed upon incorporation into a polymer matrix for pre-immobilization of the microorganisms.

Further, it is of course also possible, for example, to immobilize ligands as molecules on the surface of the polymer layer. Ligands in the context of the invention are for example molecules, such as for example proteins or ions, that can be grouped about a central structure. Ligands can be monodentate and polydentate. The term "ligands" can, however, also be understood to refer to molecules that are bound at specific sites of macromolecules, for example substrates or coenzymes to a protein. In the context of the invention, the term "molecules" or "biomolecules" may should also be understood to refer to antigens and/or antibodies. Antigens in the context of the invention are, for example, all substances that can elicit an immune response. They can be natural or synthetic macromolecules foreign to the body, in particular proteins or polysaccharides, with a molecular weight of more than 2 kilodaltons, as well as surface structures of foreign particles. An antigen according to the invention can have a high-molecular-weight part that serves as a substrate to usually a plurality of low-molecular-weight groups that govern the specificity of the immune response and the reaction of the antigens with the corresponding immunoglobulins. Antigens can be polyvalent and monovalent and thus can interact with one or with a plurality of antibody species.

It is also possible, for example, to immobilize antibodies on the support and not antigens but

antibodies. The term "antibodies" is understood, for example, to refer in particular to glycoproteins that interact specifically with one antigen. The interaction results in the formation of antigenantibody complexes. Antibodies can be for example various groups of immunoglobulins. Antibodies can be immobilized as intact antibodies or as various fragments that can be generated for example through cleavage by various peptidases. The antibodies can be modified before, or during or after immobilization on the support, for example by reduction, oxidation, or oligomerization. Further, it is also possible, for example, to use receptors as biomolecules. Receptors are for example proteins that interact with an extracellular signal molecule, for example a ligand, and activate or initiate certain functions through conformation changes, in particular via secondary messenger substances. Receptors in the context of the invention can also, however, be special cells that receive stimuli and forward the corresponding items of information; examples of this would beare photoreceptors, chemoreceptors, thermoreceptors, and baroreceptors.

The surface to which the polymer layer is applied is preferably, for example, largely planar; that is, it is a surface with low roughness such as for example surfaces of semiconductor layers or semiconductor articles with integrated circuits (IC surfaces), which, however, can display local microscopic structures that maywould be suitable for example for the receiving of biomolecules.

The term "immobilization" or "pre-immobilization" in the context of the invention should may be understood to refer, for example, to all methods for restricting the mobility and solubility of molecules by chemical, biological, and/or physical operations, the term "pre-immobilization" pertaining, for example, to all methods for fixing molecules that are carried out before immobilization by the method-according to the invention. Immobilization and/or pre-immobilization can be effected by various methods, such as, for example, the binding of molecules to one another or to supports, entrapment in the network of a polymer matrix, or enclosure by membranes. As a result

of immobilization, not only do the molecules become capable of repeated use, but after the process of interaction with the sample they can easily be separated again. They can be used in very much higher local concentrations and in continuous flow-through systems. The binding or immobilization of molecules on the support can be effected, for example, by direct attachment to the support and by crosslinking. Attachment to the support is effected in particular, for example, according to the invention, by ionic, adsorptive, or covalent binding. Cross-linking in the context of the invention is the linking of the molecules with one another or with other polymers. In immobilization by incorporation, the molecules are, for example, incorporated into gel structures or membranes before they are immobilized on the surface of the support.

There exist_individual skilled in the art will be acquainted with numerous possibilities for immobilizing molecules on the support. Here, i Immobilization may is supposed to take place in such a manner fashion that a well-defined position on the support can be assigned to every probe or molecule and every position on the support can be evaluated independently. It may, however, also be desirable for the places of deposition of various molecules or probes to overlap partially or fully or for biomolecule mixtures to be deposited. For example, immobilization can be effected by a method based on semiconductor technology. Essentially, molecules or biomolecules can be immobilized on the support in two fundamentally different ways: (a) first, the molecules can be synthesized in situ at well-defined positions on the support by successive coupling of monomeric synthetic building blocks; and (b) second, previously synthesized biomolecules, biomolecules originating in libraries, or other molecules can be laid down and immobilized at well-defined positions of the support material, which is in particular functionalized. Both spotting and printing methods can be used for this purpose. The term "spotting" is understood, for example, to refer to methods in which liquid droplets, in which the molecules are situated, are laid down on the support, substantially round spots

arising through surface interaction and drying. Other printing methods, however, also make it possible to lay down the molecules in well-defined areas on the surface of the support so that stable binding of the samples to the substrate surface of the molecules can take place with high coupling efficiency. All-Those known practices known to the individual skilled in the art for immobilizing biomolecules on, for example, column materials can likewise be put to use in order to immobilize molecules on the support.

Selected methods for immobilization or pre-immobilization are for example contact tip printing, ring and pin printing, nanoelectric printing and nanopipetting, bubble jet printing, top-spot printing, micro contact printing, Micro Fluidic Networks methods, photolithographic activation methods, photoresist lithography, electrochemical focusing, and micro wet printing. All of these methods can be applied-according to the invention.

In the context of the invention, iInorganic surfaces including metal, polypropylene, Teflon, polyethylene, polyester, polystyrene, nitride, ceramic, and/or glass can be used as the support, as can IC (integrated circuit) surfaces, silicon, silicon dioxide, and other surfaces. Metals in the context of the invention are may all be compounds whose coherence arises from a crystal lattice. The boundary between metals and nonmetals is fluid, so that the elements Ce, Sn, As, and Sb are also metals as used hereinin the context of the invention. Metals according to the invention may also include the metallic glasses, that is, materials that are in a metastable, largely amorphous state. Naturally, m Metallically conductive polymers are also metals as used hereinin the context of the invention. Metals in the context of the invention advantageously display in particular, for example, good strength, good hardness and wear resistance, high toughness, and good electrical and thermal conductance. Polypropylenes in the context of the invention are, for example, thermoplastic polymers of propylene. Polypropylenes are distinguished in particular by high hardness, resilience,

rigidity, and thermal resistance. Polytetrafluoroethylenes, which advantageously display good thermoplastic qualities, are for example Teflon-according to the invention. Polyethylenes are made in particular, for example, by polymerizing ethylene by essentially two distinct methods, the highpressure method and the low-pressure method. Polyethylenes produced by the high-pressure method advantageously display low density. The properties of supports that contain polypropylene are essentially determined by the nature of polyethylene as a partly crystalline hydrocarbon. Polyethylenes are advantageously practically insoluble in all usual solvents up to 60°. Advantageously, polar liquids such as alcohol, esters and ketones at room temperature cause little swelling of polyethylenes and thus of the support coating. Polyethylenes advantageously are completely indifferent to water, alkalies, and salt solutions as well as inorganic acids. Supports containing polyethylenes have, for example, very low permeability to water vapor. The support can, however, also expediently include polyesters. Polyesters in the context of the invention are, for example, compounds produced by ring-opening polymerization of lactones or by polycondensation of hydroxycarboxylic acids or of diols and dicarboxylic acids or dicarboxylic acid derivatives. Polyesters in the context of the invention also include, for example, polyester resins, polyesterimides, polyester rubbers, polyester polyols, and polyester polyurethanes. Polyesters are advantageously thermoplastics and have a marked material character. They are distinguished for example by high thermostability and can be processed into alloys with metals such as for example copper, aluminum, and magnesium.

It is also possible, however, for the support to contain ceramic. Ceramic in the context of the invention—as used herein is a collective term for compounds, in particular inorganic and predominantly nonmetallic compounds, containing more than 30 vol. % of crystalline materials. The individual skilled in the art is familiar with It is known that various ceramics or ceramic materials

that can be used as supports. Examples of these are so called stoneware, double-extruded tiles, laboratory porcelain, alumina ceramics, permanent magnet materials, silica brick, and magnesia brick. Among ceramic materials derived from clay, a distinction is made in the context of the invention herein between coarse and fine materials, fine clay ceramic materials comprising earthenware, china, stoneware, and porcelain. Special ceramic materials such as vitrified ceramics, oxide ceramics, SiC brick and melt-cast brick can also advantageously be used as supports. The support can also preferably contain, for example, glass as well. The term "glass" as used herein in the eontext of the invention refers to substances in the amorphous, noncrystalline solid state; that is, the glassy state can in the context of the invention be taken as denoteing a frozen supercooled liquid or melt. Glasses are therefore inorganic or organic, chiefly oxidic melt products that have been converted to a solid state by an introduction process without the melt-phase components crystallizing out. Naturally, eCrystals, melts, and supercooled melts, for example, are also referred to be classified as glasses as used hereinin the context of the invention. Glasses can be for example flat glass, laboratory glassware, lead crystal glass, fiberglass, optical glass fibers, and other glasses. It is also possible, of course, to use silicate-free glasses, for example phosphate glasses. The support can, however, also be such that optical glasses, that is, for example, glasses with special optical refractive indices, are used.

It goes without saying in the context of the invention that tThe surface of the support can be modified. Support modification can be effected in particular by biological, physical, and/or chemical operations. Examples of physical operations are polishing, etching, pickling, sandblasting, but also physical processes that lead to hardening, coating, heat treatment, production of protective skins, and the like. An example of surface treatment by biological action is overgrowth by microorganisms. A chemical modification of the surface of the supports includes for example treatment with acids,

bases, metal oxides, and other agents. The support surface can be modified in such a manner fashion that the molecules adhere especially well to the support or adhere in such a way that they are not modified disadvantageously in respect of their activity. Surface modification also includes, for example, coating with poly-L-lysines, aminosilanes, aldehyde silanes, epoxy groups, gold, streptavidin, reactive groups, polyacrylamide pads, immobilized nitrocellulose and/or activated aldehydes or agarose-aldehyde groups, by which in particular the following are bound: DNA, COOgroups, NH₂ groups, biotin, thiol groups, and others. Support surface modification naturally also includes, for example, treatment that leads to heightened stability and fracture strength. Classical surface modifications from histology, in particular for the immobilization of biomolecules, can of eourse-also be performed.

In one <u>exemplary</u> embodiment—of—the—invention, further semiconductor articles or semiconductor layers with integrated circuits or additional microsystems are to be applied in certain sections of the surface of the polymer layer. Suitable as the polymer layer here is in <u>a particular example</u> a polyimide that is known for such applications in semiconductor technology. Polyimides are in particular polymers with high-temperature stability; they advantageously display excellent mechanical, thermal, and electrical properties. Previously known applications of polyimide in semiconductor technology include in particular buffer layers, passivation layers, bonding layers, and dielectric interlayers on the support. Polyimides are in particular applied in liquid form and then cured. In this curing step the polyimide advantageously acquires the desired qualities. The polyimide can be lithographically textured for the applications. Of course, pPolyimide can also be used as an adhesion aid for potting material and as a buffer layer. The polyimide layer reduces, for example, the stress in silicon due to encapsulation and prevents cracks at the edges. The polyimide must in particular be is cured under very uniform temperature conditions to prevent cracking in the polyimide

and nonuniformities in color. Low oxygen values are advantageous in order, for example, to achieve good adhesion.

Polystyrene, which can also be employed as a polymer layer for immobilizing molecules-<u>in</u> an <u>embodimentaceording</u> to the invention, is a thermoplastic obtained chiefly by radical polymerization of styrene. The radical end of a growing polymer chain <u>does not</u>never attacks a double bond in the ring, because the benzene ring is an extraordinarily stable structure. A plurality of advantages for the employment of polystyrene stem from theis fact; that, for example, polystyrene is resistant to acids, alkalies and alcohol.

In a fFurther advantageous development of the invention, the hydrophobic polymer is applied to the surface, for example, only in previously defined regions.

In a further exemplary embodimentespecially preferred development, a positive and/or negative electric charge is imparted to the surface by plasma treatment; that is, the surfaces bear different charges at the most varied positions. Polymer materials in particular exist in various forms. The individual forms impose various requirements on the processing process. The accessibility of the surface to plasmas, for example, varies in dependence on the shaping of the surface. Plasma treatment of the polymer surface can advantageously increase the surface energy greatly and facilitate other processing methods. What principally happens in plasma treatment, is that the ions and radicals of the plasma react with the polymer surface and there generate functional groups that advantageously determine the surface qualities of the polymer. In particular, positive or negative charging results in better wettability and/or better binding of the biomolecules.

In a further <u>exemplary embodimentpreferred development of the invention</u>, UV-reactive molecules are covalently immobilized by irradiation with UV light. For example, photolabile protective groups on glass can be activated in positionally bound fashion for oligosynthesis through

the use of light selectively passing through a photolithographic mask. The glass is then flooded with photolabile molecules, for example DNA bases, which bind to the defined, previously irradiated array positions. Different photolithographic masks are then correspondingly utilized for the next oligo bases in the sequences, and the procedure is repeated. Thus four masks are required for each base in the sample oligo (per position). Production can thus advantageously be effected directly from known sequence databases, a standard normalization being achieved in this way.

If hydrophobic molecules, in particular biomolecules, are applied by one of the above-cited methods, for example a printing method, to the surface of the hydrophobic polymer layer, these molecules adhere to this surface through a sufficiently well-known interaction.

In one exemplary embodiment of the method according to the invention-for immobilizing molecules on the surface of the polymer layer, the surface of the polymer layer is to be activated in an oxygen plasma at least in sectional fashion, for example with the use of a conventional masking technique. In this way aldehyde groups, carboxyl groups, or hydroxide groups are formed on the surface of the polymer layer. These groups are hydrophilic and make possible covalent bonds with biomolecules applied to these activated regions, for example by printing with a solution containing the molecules. These covalent bonds are so stable that the polymer layer with the molecules immobilized thereon can subsequently be boiled in soap without disrupting the bonds. The surface is preferably activated in an embodiment only in island fashion-manner by oxygen plasma treatment, runoff of the applied solution on the surface being limited by the polymer layer regions left hydrophobic and surrounding the "islands."

In what follows, the invention will be described in greater detail with reference to exemplary embodiments without being restricted to these examples.

These and other objects, features and advantages of the present invention will become more

apparent in light of the following detailed description of preferred embodiments thereof.

DETAILED DESCRIPTION OF THE INVENTION

Example 1

Silicon sensor chips with CMOS photodiodes are covered with a layer of approximately 100 to 200 nm of polystyrene in the spin coater. To this end, the chips are coated with 200 µL of a 0.1% (w/v) solution of polystyrene in toluene for one minute at 3000 rpm in the spin coater. Next, the sensor regions (photodiodes) are printed with a protein solution in a raster-like array. Antibodies in PBS buffer are employed. The antibodies are in each case used in a concentration of 5 µg/mL. A portion of the raster is printed with antibodies conjugated with fluorescent dyes. The antibodies are incubated overnight in a moist chamber at 4°C, and the unbound antibodies are then rinsed off with PBS buffer. After washing with distilled water, the success of the immobilization is verified with the aid of a fluorescence measuring instrument. The successful binding of the antibodies to the sensor regions is demonstrated by the fluorescence of the antibodies. Next the chip is sealed by application of a reaction chamber made of PMMA. The application of the reaction chamber is effected by binding of the PMMA to the polystyrene layer. The finished structure is further stabilized by the employment of a commercially available stabilizing reagent for proteins and is ready for use.

Example 2

Silicon sensor chips with CMOS photodiodes, already on the wafer, are coated with a 5 μ m layer of polyimide. Next, the polyimide is coated with a copolymer of benzophenone methacrylate

and acrylic acid. The supports can then be printed in simple fashion with biomolecules such as DNA (5 μ M oligonucleotide in PBS buffer). Immobilization is effected by UV irradiation at 300 nm for approximately 10 minutes. The benzophenone of the copolymer forms radicals, which bond covalently to the polyimide coating as well as to the DNA. The same process can also be carried out with all other biomolecules such as proteins, in particular antibodies, peptides, sugars, lipids, and triglycerides as well as complex structures of the same.

Although the present invention has been shown and described with respect to several preferred embodiments thereof, various changes, omissions and additions to the form and detail thereof, may be made therein, without departing from the spirit and scope of the invention.

What is claimed is: